

1 μm Mono Mag NHS-Activated Beads Conjugation Kit Protocol

Introduction

Ocean Nanotech's NHS activated Mono Mag beads are superparamagnetic beads with larger surface area than Mono Mag (1 μm) to ensure their higher binding capacity than Mono Mag (1 μm). The beads are used to specifically conjugate primary amine-containing ligands with significant low non-specific binding. The protocol shown below has been used to successfully conjugate bovine serum albumin, streptavidin, and immunoglobulin to Ocean Nanotech's magnetic beads.

Kit Components and Storage

Each kit contains reagents for 4 reactions (based on 2.5 mg beads/reaction)

Kit Components	Quantity	Storage
Magnetic Beads (MN1001)	10 mg	-20°C
Resuspension Buffer (AB100)	15 mL	2 to 8°C
Quenching Buffer (QB100)	1 mL	2 to 8°C
Storage Buffer (SB100)	30 ml	2 to 8°C

Materials Required

- Target Ligands with Amine Group
- Magnetic Separator (Product ID: SuperMag Multitube Separator, Supplier: Ocean Nanotech)
- 1.5 mL Microcentrifuge Tubes

Critical Notes Before You Start

- This is a recommended protocol that works for 50 mg lyophilized powder contains 2.5 mg magnetic beads. Target protein amount may be needed to adjust to obtain desired binding capacity.
- Any other amine containing molecules (e.g. BSA) in the protein solution, including protein stabilizers, will compete with the conjugation reaction.
- Allow the magnetic beads and all reagents to come to room temperature before dissolving them.
- Dissolve the targeted proteins in the resuspension buffer. If the targeted protein is already suspended in buffer, such as PBS buffer, this solution could be used directly for conjugation.
- For any vortex steps, vortex at maximum speed to ensure mixing.

Protocol

A. Magnetic Beads Concentration Explanation

1. “2.5 mg magnetic beads” does not mean “2.5 mg lyophilized powder”. For example, the weight percentage of the magnetic beads in the lyophilized powder is 5% and 2.5 mg magnetic beads is needed, you will need 50 mg lyophilized powder.

$$\frac{2.5 \text{ mg magnetic beads}}{5\% \text{ (weight percentage)}} = 50 \text{ mg lyophilized powder}$$

B. Protein Preparation

1. Use ~0.1 mg pure protein per 1 mg beads. You may calculate the protein volume from the concentration.
2. For example, for 2.5 mg beads, you will need 0.25 mg protein. Therefore, if the protein concentration is 1 mg/mL, you will need 0.25 mL protein.

$$\frac{0.25 \text{ mg protein}}{1 \text{ mg/mL (protein concentration)}} = 0.25 \text{ mL protein}$$

C. Oligonucleotide or peptides preparation

1. Use ~20 nmol oligonucleotides or peptides per 1 mg beads. You may calculate the ligand volume from the concentration.
2. For example, for 2.5 mg beads, you will need 50 nmol Oligonucleotides or peptides.
3. Oligonucleotide can be coupled to the beads via the 5' or 3' after amino (NH₂) modification.

D. Conjugation Procedure

1. Add 1 mL resuspension buffer to the pre-packed 2.5 mg magnetic beads tube. Re-suspend the magnetic beads with vortex for 15 minutes.
Note: Do not proceed to the next step without vortexing the beads for 15 minutes.
2. Place tube into the magnetic separator and allow the activated magnetic beads to separate. Remove the supernatant and add 0.5 mL resuspension buffer. Re-suspend the magnetic beads with vortex or sonication.
Note: The magnetic beads should be completely suspended before adding proteins.
3. Add 0.25 mL targeted protein (1 mg/mL in resuspension buffer) or 50 nmol Oligonucleotides or peptides to the magnetic beads. React at room temperature for 2.5 hours with continuous mixing.
4. Add 0.1 mL quenching buffer to the magnetic beads suspension. React at room temperature for 30 minutes with continuous mixing.
5. Place the tube into a magnetic separator. Remove the supernatant after the supernatant is clear (1 to 2 minutes).
6. Add 1 mL storage buffer and re-suspend the magnetic beads with vortex or sonication.
7. Repeat steps #5 and #6 three times. Resuspend the magnetic beads in storage buffer.
8. The third resuspension is the purified protein conjugated magnetic beads. The final product can be stored for more than 12 months in the storage buffer at 2-8°C.

WARRANTIES AND DISCLAIMER

The Ocean Nanotech product (“Product”) is warranted to operate or perform in conformance with published Product specifications at the time of sale, as set forth in the Product documentation, specifications and/or accompanying package inserts (“Documentation”) and to be free from defects in material and workmanship. Unless otherwise expressly authorized in writing, Products **are supplied for research use only**. No claim of suitability for use in applications regulated by FDA is made. The warranty provided herein is valid only when used by properly trained individuals. Unless otherwise stated in the Documentation, this warranty is limited to one year from date of shipment when the Product is subjected to normal, proper and intended usage. This warranty does not extend to anyone other than the original purchaser of the Product (“Buyer”).

No other warranties, express or implied, are granted, including without limitation, implied warranties of merchantability, fitness for any particular purpose, or non-infringement. Buyer’s exclusive remedy for non-conforming Products during the warranty period is limited to replacement of or refund for the non-conforming Product(s).

There is no obligation to replace Products as the result of (i) accident, disaster or event of force majeure, (ii) misuse, fault or negligence of or by Buyer, (iii) use of the Products in a manner for which they were not designed, or (iv) improper storage and handling of the Products.

© 2016 Ocean Nanotech. All rights reserved. Unless otherwise indicated, all trademarks are property of Ocean Nanotech. Printed in the USA.