

# 50 nm Super Mag Carboxylic Acid Beads Conjugation Kit Protocol

#### Introduction

Ocean Nanotech's carboxyl functionalized magnetic beads are uniform superparamagnetic beads with high density of carboxyl group on the surface. The beads are used to specifically conjugate primary amine-containing ligands with low non-specific binding.

Briefly, the magnetic beads are activated using EDC/Sulfo-NHS followed by conjugation to amine groups that are present on the target protein/ligands. The protocol shown below has been used to successfully conjugate bovine serum albumin, streptavidin, and immunoglobulin to Ocean Nanotech's magnetic beads.

#### Kit Components and Storage

Each kit contains reagents for 4 reactions (based on 0.25 mL aliquot of magnetic beads)

Kit Components	Quantity	Storage
Magnetic Beads (SC0051)	1 mL (10 mg/mL)	2 to 8 °C, do not freeze
Activation Buffer (AB100)	15 mL	2 to 8°C
Quenching Buffer (QB100)	1 mL	2 to 8°C
Storage Buffer (SB100)	30 mL	2 to 8°C
EDC	20 mg	-20°C
Sulfo-NHS	20 mg	-20°C

## **Reagents Required**

- Magnetic Beads: 50 nm Super Mag Carboxylic Acid Beads (Product ID: SC0051)
- EDC (1-ethyl-3-(-3-dimethylaminopropyl) carbodiimide hydrochloride)
- Activation Buffer
- Quenching Buffer
- Storage Buffer

#### Materials Required

- Target ligands with Amine Group
- Magnetic Separator (Product ID: SuperMag Multitube Separator, Supplier: Ocean Nanotech)
- 1.5 mL Microcentrifuge Tubes
- Vortex
- Sonication bath

## **Critical Notes Before You Start**

- This protocol is good for 4 reactions per 1 mL magnetic beads (10 mg/mL concentration). Each reaction is based on 0.25 mL aliquot of magnetic beads.
- Resuspend the magnetic beads solution before use.
- Any other amine containing molecules (e.g. BSA) in the protein solution, including protein stabilizers, will compete with the conjugation reaction.
- Allow the EDC and the protein to come to room temperature before dissolving them.
- Dissolve the targeted proteins in the activation buffer. If the targeted protein is already suspended in buffer, such as PBS buffer, this solution could be used directly for conjugation.
- For any vortex or sonication steps, vortex at maximum speed to ensure mixing. Bath sonication is highly recommended.



#### A. Protein Preparation

- 1. Use ~0.1 mg protein per 1 mg beads. You may calculate the ligand volume from the concentration.
- 2. For example, for 2 mg beads, you will need 0.2 mg protein. Therefore, if the protein concentration is 1 mg/mL, you will need 0.2 mL protein.

0.2 mg protein

1 mg/mL (protein concentration) =0.2 mL protein

#### **B. EDC/Sulfo-NHS Solution Preparation**

- 1. Weigh out 5 mg EDC into one tube, and weigh out 5 mg Sulfo-NHS into another tube.
- 2. Each tube is good for one reaction use only and should be prepared only before immediate use. After an aliquot of the EDC solution and Sulfo-NHS solution, do not use the remaining EDC solution and Sulfo-NHS solution in the tube.
- 3. Add 0.5 mL activation buffer into the preweighed EDC tube and mix well to dissolve the solids. The desired concentration for EDC is 10 mg/mL.
- 4. Add 0.5 mL activation buffer into the preweighed Sulfo-NHS tube and mix well to dissolve the solids. The desired concentration for Sulfo-NHS is 10 mg/mL.

#### C. Conjugation Procedure

- 1. Aliquot 0.25 mL of the magnetic beads (10 mg/mL) into a 1.5 mL microcentrifuge tube and place the microcentrifuge tube in a magnetic separator.
- 2. Remove the supernatant with a pipette until the supernatant is clear. Add 0.4 mL activation buffer to the resuspend the magnetic beads.
- 3. Add 12.5 µL Sulfo-NHS solution (10mg/mL) and 12.5 µL EDC solution (10mg/mL) to the magnetic beads solution.
- 4. React at room temperature for 15 mins with continuous mixing. Add 0.25 ml targeted protein (1 mg/ml in activation buffer) in activation buffer to the magnetic beads.
- 5. React at room temperature for 2.5 hours with continuous mixing. Note: The amount of EDC and targeted ligands may be needed to be optimized to obtain desired binding capacity.
- 6. Add 0.1 mL quenching buffer to the magnetic beads suspension and React at room temperature for 30 minutes with continuous mixing.
- 7. Place the tube in a magnetic separator and wait 2 to 8 hours (depending on the strength of the magnetic field of the magnetic separator) for the beads to separate.
- 8. Remove the supernatant and add 1 mL storage buffer. Re-suspend the magnetic beads with vortex or sonication.
- 9. Repeat steps #6 and #7 three times. Resuspend the magnetic beads in storage buffer.
- 10. The third resuspension is the purified magnetic beads. The final product can be stored for more than 12 months in the storage buffer at 2-8°C.

#### WARRANTIES AND DISCLAIMER

The Ocean Nanotech product ("Product") is warranted to operate or perform in conformance with published Product specifications at the time of sale, as set forth in the Product documentation, specifications and/or accompanying package inserts ("Documentation") and to be free from defects in material and workmanship. Unless otherwise expressly authorized in writing, Products are supplied for research use only. No claim of suitability for use in applications regulated by FDA is made. The warranty provided herein is valid only when used by properly trained individuals. Unless otherwise stated in the Documentation, this warranty is limited to one year from date of shipment when the Product is subjected to normal, proper and intended usage. This warranty does not extend to anyone other than the original purchaser of the Product ("Buyer")

#### No other warranties, express or implied, are granted, including without limitation, implied warranties of merchantability, fitness for any particular purpose, or noninfringement. Buyer's exclusive remedy for non-conforming Products during the warranty period is limited to replacement of or refund for the non-conforming Product(s).

There is no obligation to replace Products as the result of (i) accident, disaster or event of force majeure, (ii) misuse, fault or negligence of or by Buyer, (iii) use of the Products in a manner for which they were not designed, or (iv) improper storage and handling of the Products.

© 2016 Ocean Nanotech. All rights reserved. Unless otherwise indicated, all trademarks are property of Ocean Nanotech. Printed in the USA.